



COATINGS & SEALANTS

SPEC SHEET v2023



DURABILITY	3 years + *	3 years +	2 years +	2 years	18 months	1 year	1 year	1 year	1 year	6 months	1 year	6 months	3 months	1 month	3 months	1 year	1 month
PH-RESISTANCE	2-14	3-13	3-13	3-13	3-12	3-13	5-12	5-12	5-12	5-12	5-12	5-12	6-7	6-7	5-12	5-12	
FLASHING TIME / 20°C	5 min	3 - 4 min	3 - 5 min	30 - 60 sec	3 - 5 min	instant	30 - 60 sec	1 - 2 min	2 - 3 min	instant	instant	-	-	-	10 sec	30 sec	30 - 60 sec
MIN AND MAX TIME BETWEEN LAYERS	1 h	4 h	4 h	1 h	1 h	1 h	1 h	1 h	1 h	4 h	-	-	-	-	4 h	1 h	
DRYING TIME UNTIL WATER CONTACT	4 h / 8 h **	24 h	24 h	24 h	3 h	0	0	0	24 h	24 h							
DRYING TIME UNTIL FULL HARDNESS	7 days	7 days	24 h	0	0	0	0	7 days	7 days								
IR LAMP IMPROVEMENT	yes	no	no	yes	no	no	no	yes	yes								
IR TIME & TEMP	10 min / 60°C	-	-	10 min / 60°C	-	-	-	10 min / 60°C	10 min / 60°C								
HARDNESS IMPROVEMENT	+4 H	+2 H	+2 H	+2 H	+2 H	0	0	0	0	0	0	0	0	0	0	0	
WATER SPOT VULNERABILITY	medium	low	low	low	low	low	high	low	low	medium	low	low	medium	medium	medium	medium	
REMOVABLE WITH	polishing	polishing	polishing	polishing	polishing	polishing	high pH clean	polishing	solvent mix	high pH brush	IPA 100%	high pH clean	high pH clean	high pH clean	high pH clean	polishing	
GLOSS	high	high	high	high	high	medium	-	high	high	low	low	-	high	high	high	-	
SMOOTHNESS	low	high	high	medium	medium	medium	medium	high	high	high	-	high	high	high	medium	low	

*CQUARTZ when used as a base coat for CQFR / PRO, extends their durability and warranty by 2 years. ** Above 20°C / Below 20°C.

NOTE: Specification may vary depending on temperature and humidity.